

Prílohy

Tab. 15 Hmotnosti a vlhkosť bukových teliesok o rozmeroch 15 x 25 x 50mm

Č. V.	Hmotnosť pri w = 0% (g)	Hmotnosť po degradácii (g)	Vlhkosť po degradácii (%)
44	10,11	14,3	41,44
48	9,22	14,41	56,29
49	8,47	13,83	63,28
50	9,36	15,25	62,92
51	7,96	16,33	105,15
52	8,92	14,03	57,28
53	11,86	17,38	46,54
54	10,44	16,45	57,56
55	6,99	17,58	151,50
56	12,02	15,75	31,03
57	11,35	16,84	48,37
58	9,81	18,32	86,74
59	7,86	13,68	74,04
60	8,66	14,46	66,97
61	9,07	16,53	82,24
62	11,63	17,64	51,67
64	8,01	13,55	69,16
65	7,79	13,34	71,24
66	10,11	13,71	35,61
67	9,55	13,58	42,19
68	9,26	12,71	37,25
71	10,75	14,06	30,79
72	10,58	14,89	40,73
74	7,41	13,8	86,23
75	9,09	12,99	42,90
76	9,19	12,62	37,32
78	10,6	14,02	32,26
79	9,36	13,4	43,16
80	9,85	17,35	76,14
81	9,09	13,66	50,27
82	10,88	14,18	30,33

Tab. 16 Vlhkosti BK preglejok v nasýtenej vodnej pare

Dni	Vlhkosť		
	BK nepoškodené	BK plošne poškodené	BK vryp
0	10,95635	11,06288	10,8877
1	11,149	11,34069	11,11586
2	11,37591	11,58316	11,36042
3	11,55945	11,798998	11,55222
4	11,75591	12,05725	11,76913
5	12,18464	12,56472	12,23615
6	12,39018	12,79968	12,45657
7	12,5741	13,00218	12,65044
8	12,96324	13,42859	13,41773
9	13,19503	13,82706	13,65455
11	13,52578	14,18009	14,02902
13	13,87435	14,55822	14,39022
15	14,23026	14,91737	14,74888
19	14,95454	15,67622	15,51745
23	15,63484	16,34469	16,21945
27	16,24511	16,91486	16,49319
30	16,5534	17,35456	16,92748
34	17,40079	17,80991	17,12524
37	18,4261	18,48359	17,71963
41	19,02491	19,04008	18,3184
44	19,52061	19,48468	18,77072
48	20,12996	20,1147	19,37651
51	20,46629	20,44259	19,7162
55	20,80262	20,77048	20,05589
58	21,35575	21,3562	20,68849

Tab. 1 Vlhkosti BK preglejok v nasýtenej vodnej pare

Dni	Vlhkosť		
	BR nepoškodené	BR plošne poškodené	BR vryp
0	11,42919	11,10791	11,25076
1	11,6483	11,4011	11,50439
2	11,91259	11,68229	11,78764
3	12,15644	11,90547	12,0018
4	12,37601	12,18369	12,2646
5	12,89335	12,76207	12,82691
6	13,13758	13,05582	13,09981
7	13,30129	13,29827	13,3433
8	13,73846	13,84407	13,79767
9	14,00695	14,14096	14,13191
11	14,25868	14,60586	14,5755
13	14,79278	15,04407	15,03341
15	15,19527	15,45056	15,4568
19	16,08498	16,38792	16,38766
23	16,89803	17,25087	17,22635
27	17,60423	17,95451	17,95251
30	18,13036	18,81256	19,41591
34	18,55175	19,77009	20,46655
37	18,98767	20,82695	22,18291
41	19,27217	22,16199	22,94995
44	19,4693	22,763	23,53989
48	19,75785	23,46365	24,3675
51	20,27599	23,91723	24,86166
55	20,79719	24,37083	25,57386
58	20,94862	25,08304	26,77081

Tab. 18 Vlhkosti BK preglejok v destilovanej vode

Vlhkosť			
Deň	BK nepoškodené	BK plošne poškodené	BK vryp
0	10,95444	12,10165	10,69643
1	14,79461	15,62458	14,56931
2	16,37246	17,98025	16,33848
3	17,1268	19,55782	17,43874
4	17,92101	21,02664	18,42315
5	18,61565	22,37088	19,35533
6	19,20823	23,60436	20,29299
7	19,65125	24,84756	21,17684
8	19,81318	25,80037	21,97364
9	20,01863	26,85268	22,81205
11	20,8331	28,30876	24,08518
13	21,51415	29,35975	25,07785
15	22,34321	31,00961	26,46257
19	23,63188	32,48074	28,24509
23	24,61207	34,05874	29,775
27	25,53107	35,06424	30,76041
30	25,95329	35,95113	31,48854
33	26,0781	36,40002	32,40494
37	26,27392	37,26689	33,85924
41	26,46974	38,17801	35,22922
44	26,68849	39,41045	35,77944
48	26,8775	40,37484	36,54088
51	26,90289	40,98866	36,62414
55	27,0719	42,12557	37,2021
58	27,95554	42,73864	37,98405

Tab. 2 Vlhkosti BR preglejok v destilovanej vode

Vlhkosť			
Deň	BR nepoškodené	BR plošne poškodenie	BR vryp
0	11,5875	11,47763	11,39943
1	12,37089	13,85875	13,192
2	12,9841	15,14996	14,39982
3	13,44375	16,05335	15,24311
4	13,7966	16,92074	16,07829
5	14,16435	17,64085	16,89269
6	14,52092	18,31545	17,66022
7	15,50602	19,70065	18,34602
8	15,78781	20,27937	18,94792
9	16,26185	21,08495	19,58054
11	17,02207	22,69913	21,01379
13	17,61449	23,76422	22,24299
15	18,29139	25,57688	23,63357
19	19,40019	27,24937	25,80477
23	20,30794	29,85111	27,56366
27	21,46797	31,92263	29,16939
30	22,25791	33,54925	31,24209
33	22,84346	35,82789	32,50246
37	22,95805	38,53815	33,26614
41	23,12815	40,03828	33,62572
44	23,3896	41,17966	33,95319
48	23,58954	42,1557	34,23109
51	23,74363	42,71671	34,46795
55	24,59777	43,28775	34,84997
58	25,28861	45,13098	35,42606

Tab. 20 Úbytok vlhkosti BK preglejok - navlhavosť

Vlhkosť			
Deň	nepoškodené	plošne poškodené	vryp
0	16,55334	17,35456	16,92748
3	15,83970	16,43390	16,25052
5	15,57873	16,07782	15,89259
7	15,39116	15,81782	15,65891
9	15,24049	15,66530	15,47176
11	15,01129	15,48780	15,32559
14	14,84020	15,30239	15,13799
18	14,58161	15,12909	14,95404
21	14,28845	15,07632	14,81484
25	13,97985	14,90302	14,63089
28	13,60700	14,57931	14,22688

Tab. 21 Úbytok vlhkosti BR preglejok - navlhavosť

Vlhkosť			
Deň	nepoškodené	plošne poškodené	vryp
0	18,13036	18,51256	18,41591
3	17,24471	17,38329	17,63186
5	16,90010	16,89745	17,20966
7	16,59764	16,57523	16,88549
9	16,37231	16,30610	16,61390
11	16,17106	16,08077	16,37995
14	15,88258	15,79585	16,07671
18	15,62529	15,55114	15,81570
21	15,44063	15,38939	15,71261
25	15,18334	15,14468	15,45168
28	14,80660	14,74359	15,11126

Tab. 22 Úbytok vlhkosti BK preglejok - nasiakavosť

Vlhkosť			
Deň	nepoškodené	plošne poškodené	vryp
0	25,61495	35,49439	30,57532
3	24,35105	28,98665	26,84633
5	23,13223	26,68700	25,11228
7	22,16924	24,87645	23,75914
9	21,32687	23,30660	22,56537
11	20,64929	22,01233	21,54894
14	19,82076	20,42839	20,37384
18	18,97789	19,15631	19,15679
21	18,44168	18,38382	18,34485
25	17,59881	17,11174	17,12779
28	17,44938	17,02005	17,06720

Tab. 23 Úbytok vlhkosti BR preglejok - nasiakavosť

Vlhkosť			
Deň	nepoškodené	plošné poškodenie	vryp
0	22,65319	30,82006	30,47493
3	21,61103	25,18129	27,74441
5	20,72565	23,35001	26,21836
7	20,07261	21,97918	24,97325
9	19,46591	20,76553	23,85107
11	18,94119	19,85191	22,98376
14	18,38564	18,67710	21,79467
18	17,59171	17,45262	20,65054
21	17,16407	16,76282	19,98501
25	16,37014	15,53834	18,84088
28	16,00952	15,04382	18,50485